



VRLA Rechargeable Battery

BPS5-6 (BPS5-6FR)

FEATURES

- Maintenance free(no water topping-up required)
- No free acid(Non-spillable battery)
- Can be used in any orientation(excluding used inverted)
- Absorbent Glass Mat technology for efficient gas recombination

APPLICATION

- UPS
- Fans
- Electronic Toy-Cars
- Emergency Lights
- Rechargeable Flashlights



SPECIFICATIONS


Nominal Voltage	6V	
Nominal Capacity	20 Hour Rate (250mA, 5.25V)	5.00 Ah
	10 Hour Rate (475mA, 5.25V)	4.75 Ah
	5 Hour Rate (850mA, 5.25V)	4.25 Ah
	1 Hour Rate (3000mA, 4.65V)	3.00 Ah
Approx. Weight	950g(2.09lbs.)	
Terminals	T1 (Faston Tab 187) T2 is optional	
Max. Discharge Current	75 A (5 sec.)	
Max. Charge Current	1.50 A	
Operating Temperature Range	Charge	0°C~40°C(32°F~104°F)
	Discharge	-20°C~50°C(-4°F~122°F)
	Storage	-20°C~40°C(-4°F~104°F)
Self Discharge	< 3% per month (25°C)	
Internal Resistance	≤ 13.5mΩ (Fully Charged)	

CONTAINER MATERIAL


- BPS5-6:
ABS: UL 94-HB (Dark gray color)
- BPS5-6FR:
ABS: UL 94-V0 (Light gray color)

 ISO 9001	 ISO 14001
 MH19884 UL	 CAM20310-2474-E-16 CE
<ul style="list-style-type: none"> ● IEC61056 ● GB/T 19639 	<ul style="list-style-type: none"> ● JIS C 8702


OUTER DIMENSIONS mm(inch)	Length (L)	Width (W)	Container Height (H)	Total Height (TH)
	70±1.5(2.76±0.06)	48±1.5(1.89±0.06)	102±1.5(4.02±0.06)	107±2.0(4.21±0.08)




TERMINAL TYPE



BPS5-6 (BPS5-6FR) discharge characteristics (25°C /77°F)




Battery Charging Characteristics



Charging Procedure

Application	Charging method	Charging Voltage at 25°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C /cell)	Max. charging current (CA)	Charging time 0.1CA, 25°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	

Effect Of Temperature On Long Term Float Life



Constant power discharge characteristics at 25 °C/77 °F Unit: W

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	30 Min	1 Hr	3 Hr	5 Hr	10 Hr	20 Hr
1.80V	90.4	66.5	53.3	31.7	18.20	7.29	5.02	2.808	1.478
1.75V	104.6	72.1	55.8	32.9	18.74	7.43	5.10	2.850	1.500
1.70V	111.2	74.7	57.5	33.7	19.08	7.50	5.13	2.864	1.506
1.65V	116.2	76.5	58.8	34.2	19.31	7.55	5.15	2.873	1.512
1.60V	120.0	78.0	60.0	34.5	19.50	7.60	5.16	2.873	1.512

Constant current discharge characteristics at 25 °C/77 °F Unit: A

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	30 Min	1 Hr	3 Hr	5 Hr	10 Hr	20 Hr
1.80V	16.29	11.71	9.27	5.38	3.06	1.21	0.837	0.468	0.246
1.75V	19.20	12.69	9.70	5.58	3.15	1.24	0.850	0.475	0.250
1.70V	20.40	13.15	10.00	5.71	3.21	1.25	0.855	0.477	0.251
1.65V	21.31	13.46	10.23	5.79	3.24	1.26	0.858	0.479	0.252
1.60V	22.02	13.73	10.43	5.85	3.28	1.27	0.860	0.479	0.252

All data shall be changed without prior notice, BB reserves the right to explain and update the information contained hereinto.

For Sader A/0 REV. Feb. 2010

USA:
 B&B BATTERY(USA) INC.
 6415 RANDOLPH ST.COMMERCE, CA,90040 U.S.A.
 TEL:1-323-278-1900.1-800-278-8599
 FAX:1-323-278-1268
 E-Mail:sales@bb-battery.com

CHINA FACTORY:
 B.B. BATTERY CO., LTD.
 CHENG DONG TRIAL AREA,HUANG GANG,
 RAOPING, GUANG DONG,CHINA,515700
 TEL:86-768-7601001-2
 FAX:86-768-7601469
 E-Mail:maggy@bb-battery.com

EUROPE:
 B&B BATTERY(EUROPE) B.V.
 HAAKSBERGWEG 33, 1101 BP
 AMSTERDAM, THE NETHERLANDS
 TEL: +852-91282711
 MOBILE: +852-91282711
 E-Mail: dliu@bb-battery.com

HONG KONG:
 NATIONAL TRADING LTD.
 TEL:852-2301-3800
 FAX:852-2739-1182
 E-Mail:bbhk@hkstar.com

JAPAN:
 B&B BATTERY(JAPAN) CO., LTD.
 1375-11 NARAHARA-MACHI,HACHIOJI,
 TOKYO 193-0803,JAPAN.
 TEL:81-426-25-6375
 FAX:81-426-25-6375
 E-Mail:miyata@bb-battery.com

TAIWAN:
 B.B. BATTERY(TAIWAN) CO., LTD.
 TEL:886-6-502-5150
 FAX:886-6-589-8087
 E-Mail:maggy@bb-battery.com